



Data sheet

Protection plate

Item no. 10000-10001

Composition: PEMD regrind
Colour: Neutral
Processing: Extrusion
Additive: Chalk 2%
MasterBatch: Black 2%

Typical properties

Testing	Testing standard	Test condition	Value	Unit
Density	DIN EN ISO 1183	23°C	0,53-0,90	g/cm ³
Tensile strength	DIN EN ISO 527	1mm/min	16-18	MPa

Specifications

Purpose of use	Surface protection
DIM wideness dimension	1150mm
DIM thickness dimension	10mm
DIM length dimension	2000-3000mm
Recycling rate	100%

Note:

The data listed in this document are based on our current state of knowledge. Specific specifications cannot be guaranteed nor can the suitability for specific applications be deduced from above data. The client is committed to convince himself of the suitability of the product. The data do not release the client from the obligation to sustain a qualified receipt control. Storage temperature of 25°C maximum product keeps stable for at least 24 months.

LETBÆK PLAST A/S

31-03-2016, Denmark, Product Management.